



## HOOK F.R.T.

### Construction characteristics

Basic construction  
Base material  
Standard binder backing

Width : < 50 mm  
          ≥ 50 mm  
          ≥ 100 mm

Overall thickness

Weight

### Usage characteristics

Peel Strength with Hook std \*

Shear Strength with Hook std \*

Cycle life \*

Breaking Strength \*

Shrinkage after washing (3 x 60°C) \*

Colourfastness to rubbing ISO 105 sec/X12  
Colourfastness to water ISO 105 sec/EO1  
Colourfastness to sea water ISO 105 sec/EO2  
Colourfastness to light ISO 105 sec/BO2

Colourfastness to perspiration ISO 105 sec/EO4

### Flammability test according F.A.R. 25853

Burn length  
Combined after flame and glow time  
Flaming time of drips

\* Internal norm of VESA

Woven  
Polyamide  
Polyurethane F.R.T.

Nominal ± 1 mm  
Nominal ± 1.5 mm  
Nominal ± 2 mm

1.70 – 2.05 mm

300 g/m<sup>2</sup> ± 10 %

Average 2.0 N/cm  
Minimum 1.3 N/cm

Average 10.3 N/cm<sup>2</sup>  
Minimum 7.3 N/cm<sup>2</sup>

50 % loss after 5000 cycles

Minimum 210 N/cm

Maximum 4 %

4 minimum  
4 minimum  
4 minimum  
5 minimum (dark colours)  
4 minimum (white and light colours)  
4 minimum

≤ 200 mm  
≤ 15 seconds  
≤ 5 seconds

The information included in this Technical Sheet is based on reliable tests and trials. Average value as a reference only, not a nominal specification. Given the diversity of uses of our products we advise our customers to assure themselves that the product meets the requirements of their application. The responsibility for the application and use of the product remains with the customer.

Elaborado: J.C. Lima

Revisado: E. Ducet

Autorizado: J. Jacobs

Fecha: 27.09.11

ANEXO: IDT – 605-B

FTP 101 Versión 3

**INSTRUCCIONES DE TRABAJO**

Versión nº: 2 Fecha de revisión: Septiembre 2011  
 IDT-605: Fichas técnicas de producto



# TECHNICAL DATA

## LOOP F.R.T.

### Construction characteristics

Basic construction  
 Base material  
 Standard binder backing

Width : < 50 mm  
 ≥ 50 mm  
 ≥ 100 mm

Overall thickness

Weight

### Usage characteristics

Peel Strength with Hook std \*

Shear Strength with Hook std \*

Cycle life \*

Breaking Strength \*

Shrinkage after washing (3 x 60°C) \*

Colourfastness to rubbing ISO 105 sec/X12  
 Colourfastness to water ISO 105 sec/EO1  
 Colourfastness to sea water ISO 105 sec/EO2  
 Colourfastness to light ISO 105 sec/BO2

Colourfastness to perspiration ISO 105 sec/EO4

### Flammability test according F.A.R. 25853

Burn length  
 Combined after flame and glow time  
 Flaming time of drips

\* Internal norm of VESA

Woven  
 Polyamide  
 Polyurethane F.R.T.

Nominal ± 1 mm  
 Nominal ± 1.5 mm  
 Nominal ± 2 mm

2.35 ± 0.25 mm

300 g/m<sup>2</sup> ± 10 %

Average 2.0 N/cm  
 Minimum 1.3 N/cm

Average 10.3 N/cm<sup>2</sup>  
 Minimum 7.3 N/cm<sup>2</sup>

50 % loss after 5000 cycles

Minimum 210 N/cm

Maximum 4 %

4 minimum  
 4 minimum  
 4 minimum  
 5 minimum (dark colours)  
 4 minimum (white and light colours)  
 4 minimum

≤ 200 mm  
 ≤ 15 seconds  
 ≤ 5 seconds

The information included in this Technical Sheet is based on reliable tests and trials. Average value as a reference only, not a nominal specification. Given the diversity of uses of our products we advise our customers to assure themselves that the product meets the requirements of their application. The responsibility for the application and use of the product remains with the customer.

**Elaborado:** J.C. Lima

**Revisado:** E. Ducet

**Autorizado:** J. Jacobs

Fecha: 27.09.11

ANEXO: IDT – 605-B

FTP 201 Versión 3