

## ProRox MA 960 TN<sup>SC</sup>



Old name: Insulation jacket / Pudemätte

### Product description

Stabile matt with high tensile strength - as insulation core for Insulation Jackets.

### Product properties

	Performance												Norms
Thermal conductivity	T (°C)	50	100	150	200	250	300	350	400	500	600	640	EN 12667
	λ (W/mK)	0,039	0,045	0,052	0,060	0,070	0,082	0,094	0,108	0,140	0,177	0,193	
Maximum Service Temperature	660 °C												EN 14706
Reaction to fire	Euroclass A1, for the wool only												EN 13501-1
Nominal density	95 kg/m <sup>3</sup>												EN 1602
Water Absorption	< 1 kg/m <sup>2</sup>												EN 1609
Water vapour diffusion resistance	μ = 1												EN 14303